

Product Data Sheet

Polypropylene BorECO™ BA212E

Polypropylene Block Copolymer for Non-Pressure Pipes

DESCRIPTION

BorECO BA212E is a high molecular weight, low melt flow rate polypropylene block copolymer (PP-B) with very high stiffness (PP-B HM) and impact strength.

APPLICATIONS

BorECO BA212E is recommended for solid wall and structured wall non-pressure pipes (including spiral wound pipes and twin wall corrugated pipes), fittings and chambers and profiles.

PHYSICAL PROPERTIES

Property	Typical Value	Test Method
Density	900 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2.16 kg)	0,3 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.700 MPa	ISO 178
Tensile Strain at Yield (50 mm/min)	8 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	31 MPa	ISO 527-2
Charpy Impact Strength, notched (23 °C)	50 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	5 kJ/m ²	ISO 179/1eA

* Data should not be used for specification work

PROCESSING TECHNIQUES

The actual conditions will depend on the type of the equipment used and the diameter and wall thickness of the pipes produced.

Following parameters should be used as guidelines for

extrusion: Cylinder	200 - 220 °C
Head	210 - 220 °C
Die	210 - 220 °C
Melt temperature	210 - 230 °C

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borouge representative for such particulars.

STORAGE

BorECO BA212E should be stored in dry conditions at temperature below 50 °C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on physical properties of this product. More information on storage can be found in Safety Information Sheet (SIS) for this product.

SAFETY

The product is not classified as a hazardous preparation.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet
Statement on chemicals, regulations and standards
Statement on compliance to regulations for drinking water pipes

DISCLAIMER

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

May 2015