



TAIRIPRO® PP 樹脂

項目 Property	單位 Unit	試驗方法 Test Method	試驗條件 Test Condition	射出級
				K8802
熔融指數 Melt Flow Index	g/10min	ASTM D-1238	230°Cx2.16kg	2.0
降伏點抗張強度 Tensile Strength at Yield	kg/cm ² (Mpa)	ASTM D-638	23°C	270
斷裂點延伸率 Tensile Elongation at Break	%	ASTM D-638	23°C	>200
彎曲模數 Flexural Modulus	kgf/cm ²	ASTM D-790A	23°C	11,000
洛氏硬度 Rockwell Hardness	R-scale	ASTM D-785	23°C	80
Izod 衝擊強度 Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23°C 1/8"bar	NB
			-20°C 1/8"bar	10
熱變形溫度 Heat Deflection Temperature	°C	ASTM D-648	Unannealed 1/4" bar	105
收縮率 Molding Shrinkage Temperature	%	FCFC Method	23°C	1.5~1.9
比重 Specific Gravity		ASTM D-792	23°C/23°C	0.90
FDA Compliance				Yes
燃燒性 Flammability		UL-94	FileNo.E162823	HB
特性 CHARACTERISTICS	衝擊性優、抗低溫脆化、光澤性佳			

以上數值係參考 ASTM、ISO 試驗方法所測得，僅供選擇用途品級之參考。

台灣化學纖維股份有限公司-塑膠部
 電話:02-27122211/傳真:02-27131649
 地址:台北市松山區敦化北路 201 號
 網址:https://www.fcfc-plastics.com/



台塑關係企業
FORMOSA PLASTICS GROUP

