

Polyether bloc amide **PEBAX® 7233 SP 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SP grade has been developed to be heat and UV resistant, with improved properties compared to SN grades.

Main Characteristics	Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Water absorption at equilibrium at 20°C and 50 % RH	0.7	%	ISO 62
Water absorption at saturation 24 h in water at 23°C	0.9	%	
Melting point	174	°C	ISO 11357
Vicat point Under 1 daN	164	°C	ISO 306
Hardness Shore (*) Instantaneous After 15 s	69 61	Shore D Shore D	ISO 868
Tensile test (*) Stress at Break Strain at Break	56 >300	MPa %	ASTM D 638
Flexural modulus (*)	513	MPa	ISO 178
Charpy Impact unnotched 23°C unnotched -30°C V-notched 23°C V-notched -30°C	No break No break 15 ^(c) 10 ^(c)	kJ/m ² kJ/m ² kJ/m ² kJ/m ²	ISO 179

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

(c) = Complete Break

Processing conditions	Typical values
Drying (*): Time / Temperature	5-7 hours / 70-80°C
Injection temperature: Min / Recommended / Max	230°C / 260°C / 290°C
Mold Temperature:	25-60°C

(*) Pebax is delivered dried in sealed packaging ready to be processed. Drying is only necessary for bags opened for more than 2 hours.

DPT/TDS/53376/September 2007

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.