

PolyAlloy® PBG-7115B

PC/ABS, 15% Glass Fiber Reinforced

PROPERTIES	CONDITION	VALUE	UNIT	METHOD
<u>PHYSICAL</u>				
Specific Gravity	23°C	1.29	---	ASTM D-792
Melt Flow Index	260°C/2.16kg	18	g/10min	ASTM D-1238
Mold Shrinkage	3.2mm	0.1~0.3	%	ASTM D-955
Rockwell Hardness	23°C	R-121	---	ASTM D-785
<u>MECHANICAL</u>				
Tensile Strength @ Yield	6mm/min	830	kg/cm ²	ASTM D-638
Tensile Elongation @ Break	6mm/min	2.3	%	ASTM D-638
Flexural Strength	1.3mm/min	1,200	kg/cm ²	ASTM D-790
Flexural Modulus	1.3mm/min	45,000	kg/cm ²	ASTM D-790
Izod Impact (1/8")	Notched, 23°C	6	kg-cm/cm	ASTM D-256
<u>THERMAL</u>				
Heat Distortion Temp. (unannealed)	120°C/hr	95	°C	ASTM D-648
Vicat Softening Temp. (unannealed)	50°C/hr	100	°C	ASTM D-1525
<u>FLAMMABILITY</u>				
Flame Rating_V1		1.5	mm	UL-94
<u>PROCESSING PARAMETERS</u>				
Drying Temperature		90	°C	
Drying Time		4	Hrs	
Barrel Temperature		240~260	°C	
Mold Temperature		60~90	°C	

All figures listed here is for reference, not guaranteed.

Final revised date : 2012/12

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.