



奇菱科技股份有限公司

CHI LIN TECHNOLOGY CO., LTD.

台南縣仁德鄉德崙路 71 號 電話(Tel.) : +886-6-2794113 傳真(Fax.): +886-6-2791194

NO.71, TE LUN RD., JEN TE HSIANG, TAINAN COUNTY 717, TAIWAN R.O.C.

PolyAlloy® XTG-3150

PC/PET, Glass Fiber Reinforced

PROPERTIES	CONDITION	VALUE	UNIT	METHOD
<u>PHYSICAL</u>				
Specific Gravity	23°C	1.33	---	ASTM D-792
Melt Flow Index	300°C/1.2kg	18	g/10min	ASTM D-1238
Mold Shrinkage	3.2mm	0.1-0.3	%	ASTM D-955
Rockwell Hardness	23°C	R-122	---	ASTM D-785
<u>MECHANICAL</u>				
Tensile Strength @ Yield	6mm/min	850	kg/cm ²	ASTM D-638
Tensile Elongation @ Break	6mm/min	5	%	ASTM D-638
Flexural Strength	1.3mm/min	1200	kg/cm ²	ASTM D-790
Flexural Modulus	1.3mm/min	40000	kg/cm ²	ASTM D-790
Izod Impact (1/8")	Notched, 23°C	5	kg-cm/cm	ASTM D-256
<u>THERMAL</u>				
Heat Distortion Temp. (unannealed)	120°C/hr	133	°C	ASTM D-648
Vicat Softening Temp. (unannealed)	50°C/hr	141	°C	ASTM D-1525
<u>FLAMMABILITY</u>				
Flammability_V2		1.5	mm	UL-94
<u>PROCESSING PARAMETERS</u>				
Drying Temperature		120	°C	
Drying Time		4	Hrs	
Barrel Temperature		250~280	°C	
Mold Temperature		50~90	°C	

All figures listed here is for reference, not guaranteed.

Final revised date : 2010/09