



STYRON A-TECH 1300

High-Impact Polystyrene Resins

STYRON® A-TECH® 1300 advanced technology polystyrene resin is a high-impact polystyrene resin offering excellent toughness and strength with good processability.

Main Characteristics

- Excellent toughness
- High strength
- Easy processing
- Gas-assist molding
- High heat
- UL94HB

- FDA compliant⁽¹⁾

Applications

- TV
- Printers
- Audio enclosures
- Small appliances

Properties ⁽²⁾	Test Method	English Value	English Units	S.I. Value	S.I. Units	Metric Value	Metric Units
Physical							
Melt Flow Rate (200°C/5 kg)	ASTM D 1238	4.5	g/10 min	4.5	g/10 min	4.5	g/10 min
Specific Gravity	ASTM D 792	1.04		1.04		1.04	
Linear Thermal Expansion (10 ⁻⁵)		4.2	in/in/°F	7.6	cm/cm/°C	7.6	cm/cm/°C
Mold Shrinkage	ASTM D 955	0.004 - 0.007	in/in	0.004 - 0.007	cm/cm	0.004 - 0.007	cm/cm
UL94 Classification ⁽³⁾ @ 1.5 mm		HB		HB		HB	
Injection Molded Properties							
Mechanical							
Yield Tensile Strength	ASTM D 638	4,000	psi	28	MPa	282	kg/cm ²
Ultimate Tensile Strength	ASTM D 638	4,000	psi	28	MPa	282	kg/cm ²
Ultimate Elongation	ASTM D 638	50	%	50	%	50	%
Flexural Strength	ASTM D 790	7,300	psi	50	MPa	514	kg/cm ²
Flexural Modulus	ASTM D 790	291,000	psi	2,007	MPa	20,493	kg/cm ²
Notched Izod @ 23°C	ASTM D 256	2.4	ft-lb/in	128	J/m	13.0	kg-cm/cm
Compression Molded Properties							
Mechanical							
Yield Tensile Strength	ASTM D 638	3,500	psi	24	MPa	246	kg/cm ²
Ultimate Tensile Strength	ASTM D 638	2,800	psi	19	MPa	197	kg/cm ²
Ultimate Elongation	ASTM D 638	45	%	45	%	45	%
Flexural Strength	ASTM D 790	6,100	psi	42	MPa	430	kg/cm ²
Flexural Modulus	ASTM D 790	261,000	psi	1,800	MPa	18,380	kg/cm ²
Notched Izod @ 23°C	ASTM D 256	2	ft-lb/in	107	J/m	10.9	kg-cm/cm
Thermal							
Vicat Softening Point	ASTM D 1525	221	°F	105	°C	105	°C
Deflection Temperature Under Load @ 1.82 MPa, unannealed	ASTM D 648	167	°F	75	°C	75	°C
Deflection Temperature Under Load @ 1.82 MPa, annealed	ASTM D 648	210	°F	99	°C	99	°C

(1) When used unmodified for food contact applications, this resin will comply with Food Additive Regulation 21 CFR 177.1640 under the US Food, Drug, and Cosmetic Act as amended. The uses cited above are subject to Good Manufacturing Practices and any limitations that are part of the regulations. The regulations should be consulted for complete details.

(2) Typical properties; not to be construed as specifications.

(3) This numerical flammability rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

Safety and Handling Considerations

Material Safety Data (MSD) sheets for STYRON® polystyrene resins are available from Styron Asia Limited (SAL). MSD sheets are provided to help customers satisfy their own handling, safety, and disposal needs, and those that may be required by locally applicable health and safety regulations. MSD sheets are updated regularly, therefore, please request and review the most current MSD sheet before handling or using any product.

The following comments are general and apply only to STYRON polystyrene resins as supplied.

Various additives and processing aids used in fabrication and other materials used in finishing steps have their own safe use profile and must be investigated separately.

Hazards and Handling Precautions

STYRON polystyrene resins have a very low degree of toxicity and under normal conditions of use should pose no unusual problems from ingestion, eye, or skin contact. However, caution is advised when handling, storing, using, or disposing of these resins and good housekeeping and controlling of dusts are necessary for safe handling of product. Workers should be protected from the possibility of contact with molten resin during fabrication.

Handling and fabrication of plastic resins can result in the generation of vapors and dusts. Dusts resulting from sawing, filing, and sanding of plastic parts in post-molding operations may cause irritation to eyes and the upper respiratory tract. In dusty atmospheres, use an approved dust respirator.

Pellets or beads may present a slipping hazard. Good general ventilation of the polymer processing area is recommended. Processing may release fumes which may include polymer fragments and other decomposition products. Fumes can be irritating. At temperatures exceeding melt

temperature, polymer fragments can occur. Good general ventilation should be sufficient for most conditions. Local exhaust ventilation may be necessary for some operations.

Use safety glasses. If there is a potential for exposure to particles which could cause mechanical injury to the eye, wear chemical goggles. If vapor exposure causes eye discomfort, use a full-face respirator. No other precautions other than clean body-covering clothing should be needed for handling STYRON polystyrene resins. Use gloves with insulation for thermal protection, when needed.

Combustibility

STYRON polystyrene resins will burn and, once ignited, may burn rapidly under the right conditions of heat and oxygen supply. Do not permit dust to accumulate. Dust layers can be ignited by spontaneous combustion or other ignition sources. When suspended in air, dust can pose an explosion hazard. Dense black smoke is produced when product burns. Toxic fumes are released in fire situations.

Firefighters should wear positive-pressure, self-contained breathing apparatus and full protective equipment. Water or water fog are the preferred extinguishing media. Foam, alcohol resistant foam, carbon dioxide, or dry chemicals may also be used. Soak thoroughly with water to cool and prevent re-ignition.

Disposal

DO NOT DUMP INTO ANY SEWERS, ON THE GROUND, OR INTO ANY BODY OF WATER. For unused or uncontaminated material, the preferred options include sending to a licensed recycler, reclaimer, incinerator, or other thermal destruction device. For used or contaminated material, the disposal options remain the same, although additional evaluation may be required. All disposal methods must be in compliance with national, state and local laws and regulations.

Environment

Generally speaking, in the environment, lost pellets are not a problem, except under unusual circumstances — when they enter the marine environment. They are inert and benign in terms of their physical environmental impact, but if ingested by waterfowl or aquatic life, they may mechanically cause adverse effects. Spills should be minimized and they should be cleaned up when they happen. Plastics should not be discarded into the ocean or any other body of water.

Product Stewardship

Styron Asia Limited has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis of our Product Stewardship philosophy by which we assess the health and environmental information on our products and then take appropriate steps to protect employee and public health and the environment. Our Product Stewardship program rests with every individual involved with SAL products from initial concept and research to the manufacture, sale, distribution, and disposal of each product.

Customer Notice

SAL encourages its customers and potential users of SAL products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that SAL products are not used in ways for which they were not intended or tested, SAL personnel will assist customers in dealing with ecological and product safety considerations. Your SAL sales representative can arrange the proper contacts. SAL literature, including Material Safety Data sheets, should be consulted prior to the use of SAL products. These are available from the nearest SAL offices.

NOTICE: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and product information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Seller assumes no obligations or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Styron Asia Limited does not recommend any of its polystyrene resins, including samples, for use: (A) in any application which is intended for any internal contact with human body fluids or body tissues; (B) as a critical component in any medical device that supports or sustains human life; and (C) specifically by pregnant women or in any applications designed specifically to promote or interfere with human reproduction.



Styron Asia Limited

A polystyrene JV between Dow Chemical and Asahi Kasei

47/F, Sun Hung Kai Centre, 30 Harbour Road, Wanchai, Hong Kong
Tel: (852) 2879 7572 Fax: (852) 2827 5773 Web site: www.styronasia.com

Styron Asia Limited (SAL) is a commercial representative for STYRON® polystyrene and STYRON A-TECH® advanced technology polystyrene resins manufactured by the Dow Group Companies in Tsing Yi, Hong Kong; Map Ta Phut, Thailand; and Merak, Indonesia. In addition, SAL is a commercial representative for STYRON polystyrene resins manufactured by the Asahi Kasei Group in Japan. SAL also markets the STYRON and STYRON A-TECH products produced by SAL Petrochemical (Zhangjiagang) Co., Ltd. in China.

Copyright 2000, 2002, The Dow Chemical Company. All rights reserved.

* Trademark of The Dow Chemical Company

Form No.: PA01-569-0502SD