

# VALOX™ RESIN VX4920

REGION EUROPE

## DESCRIPTION

VALOX VX4920 is a 20% glass reinforced nucleated PBT/ASA blend with excellent mechanical properties, high dimensional stability and low density. Applications: connectors and automotive industry.

## TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	105	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	105	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	7200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	160	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5500	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	80	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	105	MPa	ISO 527
Tensile Stress, break, 5 mm/min	105	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	7200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	155	MPa	ISO 178
Flexural Stress, break, 2 mm/min	155	MPa	ISO 178
Flexural Strain, break, 2 mm/min	4	%	ISO 178
Flexural Modulus, 2 mm/min	5700	MPa	ISO 178
Hardness, H358/30	130	MPa	ISO 2039-1
Hardness, Rockwell R	118	-	ISO 2039-2
<b>IMPACT</b>			
Charpy Impact, unnotched, 23°C	55	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, unnotched, -30°C	40	kJ/m <sup>2</sup>	ISO 179/2C
Izod Impact, unnotched, 23°C	680	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	605	J/m	ASTM D 4812
Izod Impact, notched, 23°C	80	J/m	ASTM D 256
Izod Impact, notched, 0°C	75	J/m	ASTM D 256

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched, -30°C	70	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	50	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, 23°C	10	kJ/m <sup>2</sup>	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, -30°C	8	kJ/m <sup>2</sup>	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	170	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	210	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	170	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.05E-04	1/°C	ASTM E 831
Thermal Conductivity	0.25	W/m-°C	ISO 8302
CTE, -40°C to 40°C, flow	2.86E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.67E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	3.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.05E-04	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.38E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.57E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	170	°C	ISO 306
Vicat Softening Temp, Rate B/120	165	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	209	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	179	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	170	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.38	-	ASTM D 792
Filler Content	20	%	ASTM D 229

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.2 – 0.4	%	SABIC method
Mold Shrinkage, flow, 3.2 mm (5)	0.3 – 0.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow (2) (5)	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 200°C/3.8 kgf	17	g/10 min	ASTM D 1238
Melt Flow Rate, 265°C/5.0 kgf	35	g/10 min	ASTM D 1238
Density	1.38	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.76	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.27	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	17	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	30	cm <sup>3</sup> /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	175	Pa-s	ISO 11443
<b>ELECTRICAL</b>			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	28	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	24	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.4	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 1.6 mm	28	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	24	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0024	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Relative Permittivity, 50/60 Hz	3.4	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Compliant, 94HB Flame Class Rating (3)(4)	1.6	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12
<b>INJECTION MOLDING</b>			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.